

## 033501 Double-sided tissue tape



### Description:

Paper tissue is coated with strong acrylic adhesive on both sides. Bonds well to most surfaces and materials. Excellent for splicing and attaching applications.

### Construction:

Backing: Non-woven Tissue Paper from Cellulose Fibers 14 gms  
 Adhesive: Acrylic Solvent  
 Release liner: Silicone and PE Coating 125 gms

### Typical physical data:

Total Thickness (without liner):	140 + 5 micron
180° Peeling Strength to Steel Plate:	≥ 20 N/25 mm
Initial Tack (steel ball) 14#:	≤ 100 mm
Holding power:	≥ 24 hours
80 °C Heat Resistance:	≥ 30 minutes
180 °C Heat Resistance:	≥ 3 minutes

### Application:

For punching, nameplates bonding and film switches fixing.  
 For evaporator in refrigerator, symbols, badges and bonding between foam and rubber.  
 For household electric appliances and electronic apparatus.

### Remark:

1. The above data are tested under lab condition; the last standard is subject to the last confirmation between the seller and the buyer.
2. Tolerance: Weight and Thickness: ±5 %; Width: ±3 mm; Length: ±0.5 %.
3. The products should be stored at room temperature and be kept away wet and/or heat source.
4. It is essential, as with all pressure-sensitive tapes, that the surface to which the tape is applied must be clean, dry, and free of grease and oil.
5. The users should take test before application so as to ensure suitability for their special purpose and technique.

### IMPORTANT NOTICE TO PURCHASER

All statements technical information and recommendations contained herein are based on tests we believe to be reliable, but the accuracy or completeness thereof is not guaranteed and the following is made in lieu of all warranties, express or implied: Seller's and manufacturer's only obligation shall be to replace such quantity of the product proved to be defective. Neither seller nor manufacturer shall be liable for any injury, loss or damage, direct or consequential, arising out of the use of or the inability to use the product. Before using, users shall determine the suitability of the product for their intended use, and assume all risk and liability whatsoever in connection therewith. No statement or recommendation not contained herein shall have any force or effect unless in an agreement signed by officers of seller and manufacture.